

Prüfbericht-Nr.: <i>Test Report No.:</i>	89214771.01br	Auftrags-Nr.: <i>Order No.:</i>	226673	Seite 1 von 14 Page 1 of 14	
Kunden-Referenz-Nr.: <i>Client Reference No.:</i>	DEFLEXFR 575	Auftragsdatum: <i>Order date:</i>	07.02.2019		
Auftraggeber: <i>Client:</i>	Justrite Safety Group EMEA B.V., Achterzeedijk 57, 2992 SB Barendrecht, The Netherlands				
Prüfgegenstand: <i>Test item:</i>	Anti fatigue mat				
Bezeichnung / Typ-Nr.: <i>Identification / Type No.:</i>	575 De-Flex™ Nitrile FR				
Auftrags-Inhalt: <i>Order content:</i>	Classification of burning behaviour				
Prüfgrundlage: <i>Test specification:</i>	EN 13501-1:2007+ A1:2009 Classification of burning behaviour <i>Test methods: Ignitability of products subjected to direct impingement of flame (EN ISO 11925-2:2010/C1:2011) and determination of the burning behaviour using a radiant heat source (EN ISO 9239-1:2010)</i>				
Wareneingangsdatum: <i>Date of receipt:</i>	08.02.2019				
Prüfmuster-Nr.: <i>Test sample No.:</i>	MT19-226673.01				
Prüfzeitraum: <i>Testing period:</i>	08.02.2019 - 14.02.2019				
Ort der Prüfung: <i>Place of testing:</i>	Westervoortsedijk 73, 6827 AV Arnhem, Netherlands				
Prüflaboratorium: <i>Testing laboratory:</i>	TÜV Rheinland Nederland B.V.				
Prüfergebnis*: <i>Test result*:</i>	Siehe Sonstiges / See Other				
geprüft von / tested by:	kontrolliert von / reviewed by:				
21.02.2019 M.A. van de Vlekkert 	21.02.2019 R. Boerboom 				
Datum <i>Date</i>	Name / Stellung <i>Name / Position</i>	Unterschrift <i>Signature</i>	Datum <i>Date</i>	Name / Stellung <i>Name / Position</i>	Unterschrift <i>Signature</i>
Sonstiges / Other:		Test result: See clause 4 on page 5.			
Zustand des Prüfgegenstandes bei Anlieferung: <i>Condition of the test item at delivery:</i>		Prüfmuster vollständig und unbeschädigt <i>Test item complete and undamaged</i>			
* Legende: 1 = sehr gut 2 = gut 3 = befriedigend 4 = ausreichend 5 = mangelhaft P(ass) = entspricht o.g. Prüfgrundlage(n) F(ail) = entspricht nicht o.g. Prüfgrundlage(n) N/A = nicht anwendbar N/T = nicht getestet Legend: 1 = very good 2 = good 3 = satisfactory 4 = sufficient 5 = poor P(ass) = passed a.m. test specification(s) F(ail) = failed a.m. test specification(s) N/A = not applicable N/T = not tested					
Dieser Prüfbericht bezieht sich nur auf das o.g. Prüfmuster und darf ohne Genehmigung der Prüfstelle nicht auszugsweise vervielfältigt werden. Dieser Bericht berechtigt nicht zur Verwendung eines Prüfzeichens. <i>This test report only relates to the a. m. test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any test mark.</i>					

v04

Prüfbericht-Nr.: 89214771.01br
Test Report No.:

Seite 3 von 14
Page 3 of 14

Produktbeschreibung
Product description

Product identity	575 De-Flex™ Nitrile FR*	Use of fire-retardant	Yes*
------------------	--------------------------	-----------------------	------

* applicants declaration

Figure 1, Picture of the received sample



Figure 2, Picture of the received sample (back)



Prüfbericht-Nr.: 89214771.01br
Test Report No.:

Seite 4 von 14
Page 4 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

1	Construction data (indicative) of the product obtained by the testlaboratory after pre-conditioning 01-4.3-P.02-322-WI01		
	Test condition	23 ± 2°C and 50 ± 4% relative humidity	
	Pre conditioning, duration	≥ 48 h & until constant mass is achieved	
	Total thickness (mm)	17.7	
	Total mass (g/m ²)	15362	
	Density (kg/m ³)	870	
	<i>Note: the determined construction data are used for determination of constant mass, the used testmethod is not in accordance with the determination of construction data according the specification standard. Therefore the testresults should be handled as indicative.</i>		

2	Ignitability of products subjected to direct impingement of flame EN ISO 11925-2:2010/C1:2011						
	Date of testing	14.02.2019					
	Pre-conditioning, climate	23 ± 2°C and 50 ± 4% relative humidity					
	Pre-conditioning, duration	≥ 48 h & until constant mass is achieved					
	Description of substrate	Fibre cement board, thickness 8 ± 2 mm, density 1800 ± 200 kg/m ³ conforming to EN 13238:2010					
	Flame application	Surface					
	Flame application time (s)	15					
	Requirements according EN 13501-1:2007+A1:2009	See clause 5					
	Test result(s)						
	Orientation	Length			Width		
	Test sample	1	2	3	1	2	3
	Ignition of the sample	Yes	Yes	Yes	Yes	Yes	Yes
	Flame tip reached 150 mm above the application point	No	No	No	No	No	No
	Duration after application when the flame tip reached the 150 mm above the application point (s)	N/A	N/A	N/A	N/A	N/A	N/A
	Extent of damaged area, length (mm)	25	24	25	20	18	18
	Extent of damaged area, width (mm)	12	12	12	14	13	13
	Material melts	No	No	No	No	No	No
Shrinks away from flame without being ignited	No	No	No	No	No	No	
After glowing	No	No	No	No	No	No	
Flaming droplets/particles which caused ignition of filter paper	No	No	No	No	No	No	

Prüfbericht-Nr.: 89214771.01br			
Test Report No.:			
Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

3	Determination of the burning behaviour using a radiant heat source EN ISO 9239-1:2010					
	Date of testing	14.02.2019				
	Pre-conditioning, climate	23 ± 2°C and 50 ± 4% relative humidity				
	Pre-conditioning, duration	≥ 48 h & until constant mass is achieved				
	Description of substrate	Fibre cement board, thickness 8 ± 2 mm, density 1800 ± 200 kg/m ³ conforming to EN 13238:2010				
	Fixing method	None, samples are tested loose laid on the substrate				
	Requirements according EN 13501-1:2007+ A1:2009	See clause 5				
	Test result(s)					
	Test sample	1	2	3	4	Mean
	Orientation (Length: ↑, Width: T)	↑	T	T	T	T
	Flame spread (cm)	11	15	16	18	16
	CHF / HF-30 (kW/m ²)	10.5	10.0	9.9	9.6	9.8
	Maximum light attenuation (%)	34.8	35.1	37.2	38.0	36.8
	Smoke production (%.min)	285	342	379	398	373
Observations: Specimen 1, 2, 3 and 4: No flashing, transitory- or sustained flaming are observed. Specimen 1: Extinguished naturally before the end of the test duration. Specimen 2, 3 and 4: Extinguished manually after the end of the test duration.						

4	Classification of burning behaviour EN 13501-1:2007+A1:2009	
	The product, 575 De-Flex™ Nitrile FR , in relation to its reaction to fire behaviour is classified:	B_{fl}
	The additional classification in relation to smoke production is:	s1
	Reaction to fire classification : B_{fl} – s1	
	Field of application <ul style="list-style-type: none"> - As a floor covering in accordance with the nominal product parameters given on page 3. - On end use substrates of classes A1 and A2-s1,d0 according to EN 13238:2010. - Any way of fixation, glued down or loose laid. 	
	Statements <ul style="list-style-type: none"> - This document does not represent type approval or certification of the product. - The test results only relate to the behaviour of the test specimens of the examined product under the -particular conditions of the test in laboratory conditions; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use. - The validity of this report will expire directly after alterations or modifications of the examined product (combination)(s) and/or the criteria. 	

Prüfbericht-Nr.: 89214771.01br
Test Report No.:

Seite 6 von 14
Page 6 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

5	Potential classes of reaction to fire performance for floorings			
	EN 13501-1:2007+A1:2009			
	Class	Test method(s)	Classification criteria	
	A1 _{fi}	EN ISO 1182 ^a and	$\Delta T \leq 30 \text{ °C}$; and $\Delta m \leq 50 \%$; and $t_f = 0$ (i.e. no sustained flaming)	-
		EN ISO 1716	$PCS \leq 2.0 \text{ MJ/kg}^a$ and $PCS \leq 2.0 \text{ MJ/m}^2^b$ and $PCS \leq 1.4 \text{ MJ/m}^2^c$ and $PCS \leq 2.0 \text{ MJ/kg}^d$	-
	A2 _{fi}	EN ISO 1182 ^a or	$\Delta T \leq 50 \text{ °C}$ and $\Delta m \leq 50 \%$ and $t_f \leq 20 \text{ s}$	-
		EN ISO 1716 and	$PCS \leq 3.0 \text{ MJ/kg}^a$ and $PCS \leq 4.0 \text{ MJ/m}^2^b$ and $PCS \leq 4.0 \text{ MJ/m}^2^c$ and $PCS \leq 3.0 \text{ MJ/kg}^d$	-
		EN ISO 9239-1 ^e	$CHF \geq 8.0 \text{ kW/m}^2$	Smoke production ^g
	B _{fi}	EN ISO 9239-1 ^e and	$CHF \geq 8.0 \text{ kW/m}^2$	Smoke production ^g
		EN ISO 11925-2 ^h : Exposure = 15 s	$F_s \leq 150 \text{ mm}$ within 20 s	-
	C _{fi}	EN ISO 9239-1 ^e and	$CHF \geq 4.5 \text{ kW/m}^2$	Smoke production ^g
		EN ISO 11925-2 ^h : Exposure = 15 s	$F_s \leq 150 \text{ mm}$ within 20 s	-
	D _{fi}	EN ISO 9239-1 ^e and	$CHF \geq 3.0 \text{ kW/m}^2$	Smoke production ^g
EN ISO 11925-2 ^h : Exposure = 15 s		$F_s \leq 150 \text{ mm}$ within 20 s	-	
E _{fi}	EN ISO 11925-2 ^h : Exposure = 15 s	$F_s \leq 150 \text{ mm}$ within 20 s	-	
F _{fi}	No performance determined			
^a	For homogeneous products and substantial components of non-homogeneous products.			
^b	For any external non-substantial component of non-homogeneous products.			
^c	For any internal non-substantial component of non-homogeneous products.			
^d	For the product as a whole.			
^e	Test duration = 30 min.			
^f	Critical flux is defined as the radiant flux at which the flame extinguishes or the radiant flux after a test period of 30 min, whichever is the lower (i.e. the flux corresponding with the furthest extent of spread of flame).			
^g	s1 = Smoke $\leq 750 \%$ minutes; s2 = not s1.			
^h	Under conditions of surface flame attack and, if appropriate to the end use application of the product, edge flame attack.			

Prüfbericht-Nr.: 89214771.01br
Test Report No.:

Seite 7 von 14
Page 7 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

6	<p>Flooring Radiant Panel Single Specimen Report</p> <p>Report produced with the Fire Testing Technology FRPSoft software page 1</p> <h2 style="text-align: center;">Flooring Radiant Panel Single Specimen Report</h2> <p>Standard : EN ISO 9239-1:2010 Laboratory : TÜV Rheinland Nederland B.V. Sponsor : Justrite Safety Group Date of test : Feb. 14 2019</p> <p>Specimen description : 89214771 575 De-Flex Test name : Prod 1 MT19-226673.01 File name : D:\FRPFILES\19020015.CSV Test number in series : 4</p> <p>Flux calibration file name : C:\FRPSOFT2.9A\CALIB\FLX18009.CSV</p> <p>Thickness (mm) : 17.7 Density (kg/m³) : 870</p> <p>Test duration : 27 minutes 20 seconds (1640 s) Substrate used? : Yes Substrate : Calcium silicate Fixing method : none Conditioned? : Yes Conditioning temp. (°C) : 23 Conditioning RH (%) : 50</p> <p>Test Results</p> <p>Time to ignition : 2 minutes 17 seconds (137 s) Time to flameout : 27 minutes 17 seconds (1637 s) Extent of burning (mm) : 110 Critical flux at extinguishment (kW/m²) : 10.52 HF-10 (kW/m²) : 10.66 HF-20 (kW/m²) : 10.52 HF-30 (kW/m²) : Not calculated (test duration < 30 minutes) Flame spread at 10 minutes (mm) : 100 Flame spread at 20 minutes (mm) : 110 Flame spread at 30 minutes (mm) : Not measured Peak light attenuation (%) : 34.77 Time to peak light attenuation : 11 minutes 30 seconds (690 s) Total integrated smoke (%.min) : 285.21</p> <p>Potential classification : A2(fl)/B(fl) Smoke production classification : s1</p> <p>These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.</p>
----------	---


Prüfbericht-Nr.: 89214771.01br
Test Report No.:

Seite 8 von 14
Page 8 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

Report produced with the Fire Testing Technology FRPSoft software

page 2



Test name : Prod 1 MT19-226673.01
File name : D:\FRPFILES\19020015.CSV

Rake Results

Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)	Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)
60	445	11.2	4.995	510	-	3.7	-
110	700	10.5	7.361	560	-	3.1	-
160	-	9.9	-	610	-	2.7	-
210	-	9.2	-	660	-	2.3	-
260	-	8.2	-	710	-	2.0	-
310	-	7.3	-	760	-	1.6	-
360	-	6.3	-	810	-	1.4	-
410	-	5.3	-	860	-	1.3	-
460	-	4.4	-	910	-	1.2	-

Comments

Specimen extinguished naturally.

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Prüfbericht-Nr.: 89214771.01br
Test Report No.:

Seite 9 von 14
Page 9 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

Report produced with the Fire Testing Technology FRPSoft software

page 1

Flooring Radiant Panel Single Specimen Report

Standard : EN ISO 9239-1:2010
 Laboratory : TÜV Rheinland Nederland B.V.
 Sponsor : Justrite Safety Group
 Date of test : Feb. 14 2019

Specimen description : 89214771 575 De-Flex
 Test name : Cross 2 MT19-226673.01
 File name : D:\FRPFILES\19020016.CSV
 Test number in series : 4

Flux calibration file name : C:\FRPSOFT2.9\CALIB\FLX18009.CSV

Thickness (mm) : 17.7
 Density (kg/m³) : 870

Test duration : 30 minutes (1800 s)
 Substrate used? : Yes
 Substrate : Calcium silicate
 Fixing method : none
 Conditioned? : Yes
 Conditioning temp. (°C) : 23
 Conditioning RH (%) : 50

Test Results

Time to ignition : 2 minutes 15 seconds (135 s)
 Time to flameout : 30 minutes (1800 s)
 Extent of burning (mm) : 150
 Critical flux at extinguishment (kW/m²) : 10.04
 HF-10 (kW/m²) : 10.66
 HF-20 (kW/m²) : 10.04
 HF-30 (kW/m²) : 10.04
 Flame spread at 10 minutes (mm) : 100
 Flame spread at 20 minutes (mm) : 150
 Flame spread at 30 minutes (mm) : 150
 Peak light attenuation (%) : 35.12
 Time to peak light attenuation : 9 minutes 44 seconds (584 s)
 Total integrated smoke (%.min) : 341.56

Potential classification : A2(1)B(1)
Smoke production classification : s1

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.


Prüfbericht-Nr.: 89214771.01br
Test Report No.:

Seite 10 von 14
Page 10 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

Report produced with the Fire Testing Technology FRPSoft software

page 2



Test name : Cross 2 MT19-226673.01
File name : D:\FRPFILES\19020016.CSV

Rake Results

Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)	Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)
60	425	11.2	4.771	510	-	3.7	-
110	651	10.5	6.846	560	-	3.1	-
160	-	9.9	-	610	-	2.7	-
210	-	9.2	-	660	-	2.3	-
260	-	8.2	-	710	-	2.0	-
310	-	7.3	-	760	-	1.6	-
360	-	6.3	-	810	-	1.4	-
410	-	5.3	-	860	-	1.3	-
460	-	4.4	-	910	-	1.2	-

Comments

Specimen was extinguished manually after end of test.

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Prüfbericht-Nr.: 89214771.01br
Test Report No.:

Seite 11 von 14
Page 11 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

Report produced with the Fire Testing Technology FRPSoft software

page 1

Flooring Radiant Panel Single Specimen Report

Standard : EN ISO 9239-1:2010
 Laboratory : TÜV Rheinland Nederland B.V.
 Sponsor : Justrite Safety Group
 Date of test : Feb. 14 2019

Specimen description : 89214771 575 De-Flex
 Test name : Cross 3 MT19-226673.01
 File name : D:\FRPFILES\19020017.CSV
 Test number in series : 4

Flux calibration file name : CAFRPSOFT2.9A\CALIB\FLX18009.CSV

Thickness (mm) : 17.7
 Density (kg/m³) : 870

Test duration : 30 minutes (1800 s)
 Substrate used? : Yes
 Substrate : Calcium silicate
 Fixing method : none
 Conditioned? : Yes
 Conditioning temp. (°C) : 23
 Conditioning RH (%) : 50

Test Results

Time to ignition : 2 minutes 17 seconds (137 s)
 Time to flameout : 30 minutes (1800 s)
 Extent of burning (mm) : 160
 Critical flux at extinguishment (kW/m²) : 9.92
 HF-10 (kW/m²) : 10.66
 HF-20 (kW/m²) : 9.92
 HF-30 (kW/m²) : 9.92
 Flame spread at 10 minutes (mm) : 100
 Flame spread at 20 minutes (mm) : 160
 Flame spread at 30 minutes (mm) : 160
 Peak light attenuation (%) : 37.21
 Time to peak light attenuation : 11 minutes 13 seconds (673 s)
 Total integrated smoke (%.min) : 379.12

Potential classification : A2(1)/B(1)
Smoke production classification : s1


These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Prüfbericht-Nr.: 89214771.01br
Test Report No.:

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

Report produced with the Fire Testing Technology FRPSoft software

page 2



Test name : Cross 3 MT19-226673.01
File name : D:\FRPFILES\19020017.CSV

Rake Results

Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)	Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)
60	399	11.2	4.479	510	-	3.7	-
110	638	10.5	6.709	560	-	3.1	-
160	871	9.9	8.638	610	-	2.7	-
210	-	9.2	-	660	-	2.3	-
260	-	8.2	-	710	-	2.0	-
310	-	7.3	-	760	-	1.6	-
360	-	6.3	-	810	-	1.4	-
410	-	5.3	-	860	-	1.3	-
460	-	4.4	-	910	-	1.2	-

Comments

Specimen was extinguished manually after end of test.

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Prüfbericht-Nr.: 89214771.01br
Test Report No.:

Seite 13 von 14
Page 13 of 14

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

Report produced with the Fire Testing Technology FRPSoft software

page 1

Flooring Radiant Panel Single Specimen Report

Standard : EN ISO 9239-1:2010
 Laboratory : TÜV Rheinland Nederland B.V.
 Sponsor : Justrite Safety Group
 Date of test : Feb. 14 2019

Specimen description : 89214771 575 De-Flex
 Test name : Cross 4 MT19-226673.01
 File name : D:\FRPFILES\19020018.CSV
 Test number in series : 4

Flux calibration file name : C:\FRPSOFT2.9A\CALIB\FLX18009.CSV

Thickness (mm) : 17.7
 Density (kg/m³) : 870

Test duration : 30 minutes (1800 s)
 Substrate used? : Yes
 Substrate : Calcium silicate
 Fixing method : none
 Conditioned? : Yes
 Conditioning temp. (°C) : 23
 Conditioning RH (%) : 50

Test Results

Time to ignition : 2 minutes 15 seconds (135 s)
 Time to flameout : 30 minutes (1800 s)
 Extent of burning (mm) : 180
 Critical flux at extinguishment (kW/m²) : 9.63
 HF-10 (kW/m²) : 10.66
 HF-20 (kW/m²) : 9.63
 HF-30 (kW/m²) : 9.63
 Flame spread at 10 minutes (mm) : 100
 Flame spread at 20 minutes (mm) : 180
 Flame spread at 30 minutes (mm) : 180
 Peak light attenuation (%) : 38.02
 Time to peak light attenuation : 8 minutes 19 seconds (499 s)
 Total integrated smoke (%.min) : 398.02

Potential classification : A2(f)/B(f)
 Smoke production classification : s1


These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Prüfbericht-Nr.: 89214771.01br
Test Report No.:

Absatz	EN 13501-1:2007+ A1:2009	Messergebnisse - Bemerkungen	Bewertung
Clause	Anforderungen - Prüfungen / Requirements - Tests	Measuring results - Remarks	Evaluation

Report produced with the Fire Testing Technology FRPSoft software

page 2



Test name : Cross 4 MT19-226673.01
File name : D:\FRPFILES\19020018.CSV

Rake Results

Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)	Position (mm)	Time (s)	Flux (kW/m ²)	Qsb (MJ/m ²)
60	351	11.2	3.940	510	-	3.7	-
110	620	10.5	6.520	560	-	3.1	-
160	940	9.9	9.322	610	-	2.7	-
210	-	9.2	-	660	-	2.3	-
260	-	8.2	-	710	-	2.0	-
310	-	7.3	-	760	-	1.6	-
360	-	6.3	-	810	-	1.4	-
410	-	5.3	-	860	-	1.3	-
460	-	4.4	-	910	-	1.2	-

Comments

Specimen was extinguished manually after end of test.

These results relate only to the behaviour of the specimens of the product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.