406 Crossrib Sof-Tred™










• Side-to-side wide ribs provide traction and is easy to sweep clean.

- Exceptional worker comfort due to 12,7 mm thick newly formulated compound.
- Protective layer of exclusive Dyna-Shield™ extends service life by 50% compared to regular microcellular vinyl.
- Fire rating Class 2 according NFPA Safety Code 101.
- Available yellow borders along sides comply with OSHA code 1910-144.
- All 4 sides are bevelled and sealed to minimize tripping hazards.
- Free of toxic DOP and DMF.



406 Crossrib Sof-Tred[™]

	PF	RODUCT SPECIFICATIONS	
Designation	Industrial matting		
Туре	Anti-fatigue		
Description	Side-to-side wide ribs surface, with protective layer of Dyna-Shield™		
Material	Microcellular vinyl		
Process	Foaming		
Category	Better		
Recommended use	Medium duty – dry areas		
Colours	Black/Yellow, Grey		
Weight	4 kg/m ²		
Thickness	12,7 mm		
Standard sizes	60 cm x 91 cm 91 cm x 150 cm 60 cm x 18.3 m 91 cm x 18.3 m 122 cm x 18.3 m		
Custom sizes	60 cm, 91 cm and 122 cm per linear meter		
Special remarks	With Dyna-Shield™, a tou Ribs are running width-w	ugh barrier which is 50% more resis [.] rise.	tant to wear.
		PRODUCT TESTING	
Tests		Norms	Results
Compression deflection		U.S.	
	1.4 Kg/cm ²		0,71 cm
	2.8 Kg/cm ²		0,84 cm
Foam battery		ASTM D3574	
Abrasion resistance		ASTM D3884-01	
	500 Cycles		1,7% weight loss
	1000 Cycles		2,02% weight loss
Static coefficient of friction		ASTM C1028-96	1,10
Elongation		ASTM D412	144%
Breaking load		ASTM D412	22,1 lb
Graves tear strength		ASTM D 1004	10,5 lb
Hardness		ASTM D2240-02	25 Shore A
Anti-slip		DIN 51130 and BG-RULE BGR1	.81
		FIRE TESTING	
	Critical radiant flux	ASTM E-648	0.32 watts/cm ²
	Fire retardancy	DIN4102	
		EN 13501-1	
	Flammability test	ASTM D2859	Pass
ESD		ANSI ESD S7.1 50% Humidity	
Sustainability		 Recyclable material Reach Compliant (Registration, Evaluation, Authorization Restriction of Chemicals) 	

zu beziehen bei: https://matten-zuschnitt.de mail: info@matten-zuschnitt.de Tel.: 06359/9611906